

BEDDING SAND SIEVE ANALYSIS

Pavers must be laid on free draining material to ensure quick drainage of water.

Bedding sand should be coarse and angular with the grading properties detailed below.

Sieve size	Percent Passing
9.52mm	100
4.75mm	90-100
2.36mm	75-100
1.18mm	55-90
600 microns	35-59
300 microns	8-30
150 microns	0-10
75 microns	0-5

This grading will provide good drainage below the pavement and will also provide a non-plastic, sound bedding medium.

Crusher dust must not be used as bedding medium

Warranty claims will not be recognised where crusher dust is used.